

SILQUEST* VX-225 silane

SILANES - ADHESIVES & SEALANTS ADDITIVES







Silquest VX-225 silane is an amino-functional oligosiloxane adhesion promoter that may be considered for use over a broad range of adhesives and sealants applications.

Key Features and Typical Benefits

Silquest VX-225 silane can improve the performance of moisture curable hybrid sealants, room temperature vulcanization (RTV) silicones and polyurethane sealants, adhesives and coatings.

Silquest VX-225 silane not only acts as an adhesion promoter but can modify the physical properties of Hybrid and RTV sealants by increasing their elasticity, lowering modulus and decreasing residual surface tack of the final cured product. It can also help reduce yellowing in sealant formulations.

As such, the beneficial characteristics of Silquest VX-225 silane include:

- multi amino functionality for improved adhesion especially under wet conditions
- reduced VOCs of the final formulation vs typical amino silanes – reduced hazardous air pollutants (HAPs) emissions
- lower sealant viscosity to improve sealant application rate
- lower sealant residual surface tack compared to typical amino silanes
- improved elasticity and lower modulus of the cured sealant
- reduced yellowing with outdoor exposure

Typical Physical Properties			
Appearance	Clear liquid		
Color Index (Gardner)	1		
Density (g/ml)	0.99		
Refractive Index (n _D 25°C)	1.42		
Viscosity (mPas)	20		
Boiling Point (@ 1.1013 hPa), °C	266		
Flash Point (°C)	80		

Typical physical property values should not be used as specifications.

SILQUEST* VX-225 silane

Adhesion in Peel Performance of SPUR+* prepolymer-based Sealant

The following sealant formulation was used to evaluate the performance characteristics of Silquest VX-225 silane.

Ingredients	wt%
SPUR ⁺ 1015 LM Prepolymer	22.94
Plasticizer (DIDP)	18.35
Moisture Scavenger (Silquest A-171* silane)	0.34
Calcium Carbonate	55.05
UV Stabilizers	0.46
Silica	1.115
Titanium Dioxide	1.15
Adhesion Promoter	0.57
Tin Catalyst	0.03
Total	100

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

SPUR⁺ 1015 LM prepolymer is available from Momentive Performance Materials.

The physical properties of one-part SPUR+ prepolymer-based sealant using Silquest VX-225 silane were evaluated using European test methods (ISO 34, 37, 868, 4578, 9046, 7389). The adhesion in peel was measured using ASTM method C 794.

The properties of SPUR+ prepolymer-based sealant using Silquest VX-225 silane as adhesion promoter are shown in the following table. Silquest VX-225 silane appeared to outperform Silquest A-1110 silane (aminopropyltrimethoxysilane) on glass, aluminum and concrete substrates.

	Adhesion Promoter 0.57 wt%		
Physical Properties	Silquest A-1110 Silane	Silquest VX-225 Silane	
Tensile Strength (MPa)	1.29	1.23	
Elongation at Break (%)	381	1023	
Tensile Modulus at 100% (MPa)	0.67	0.32	
Shore A Hardness	30.2	23.8	
Substrate (CF = cohesive failure)			
Aluminum	3.8/100%CF	5.3/100%CF	
Glass	3.5/100%CF	4.2/100%CF	
Dry Concrete (surface smooth and flat)	2.8/100%CF	3.6/40%CF	
Dry Concrete (surface rough and porous)	2.9/100%CF	5.3/100%CF	

Note: Test data. Actual results may vary.

SILQUEST* VX-225 silane

Patent Status

Technical subject matter in this publication is described and protected by one or more of the following U.S. Patents and their foreign counterpart patents and/or patent applications: U.S. Patent No. 6,602,964. Other U.S. and foreign patents and/or patent applications not listed covering the subject matter may be relevant.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Emergency Service

Momentive Performance Materials maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC) and CareChem24 International also maintain an around-the-clock emergency service for all chemical products:

Location	Momentive Performance Materials Products	All Chemical Products
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500	CHEMTREC: 800.424.9300
Canada	518.233.2500	CHEMTREC: 800.424.9300
Europe	+518.233.2500 (Albanian, Czech, Danish, Dutch, English, Finnish, French, German, Greek, Hungarian, Italian, Lithuanian, Norwegian, Polish, Portuguese, Romanian, Russian, Serbo-Croatian, Slovak, Spanish, Swedish, Turkish, Ukrainian)	+44.(0)208.762.8322 (UK)
Middle East,		
All countries, except Israel	+518.233.2500	+961.3.487.287 (Lebanon)
Middle East, Israel	+518.233.2500	+44.(0)208.762.8322 (UK)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials at 518.233.2500 or CHEMTREC at 800.424.9300.	

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

CUSTOMER SERVICE CENTERS

North America	E cs-na.silicones@momentive.com		
	Specialty Fluids	T +1.800.523.5862	F +1.304.746.1654
	 UA, Silanes and Specialty Coatings 	T +1.800.334.4674	F +1.304.746.1623
	 RTVs and Elastomers 	T +1.800.332.3390	F +1.304.746.1623
	 Consumer Sealants & Construction Sealants and Adhesives 	T +1.877.943.7325	F +1.304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	Argentina & Chile	T+54.11.4862.9544	F +54.11.4862.9544
	Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	 Mexico & Central America 	T +52.55.2169.7670	F +52.55.2169.7699
	 Venezuela, Ecuador, Peru, 	T +58.212.285.2149	F +58.212.285.2149
	Colombia & Caribbean		
Europe, Middle East,	E cs-eur.silicones@momentive.com	T +00.800.4321.1000	
Africa and India		T +40.21.3111848	
Pacific	E cs-ap.silicones@momentive.com		
	China	T+1.800.820.0202 or	F +86.21.5079.3725
		T +86.21.3860.4892	
	Japan	T +0120.975.400 or	F +81.276.31.6259
		T +81.276.20.6182	
	 Korea 	T +82.2.6201.4600	F +82.2.6201.4601
	 Malaysia 	T +60.3.9206.1532	F +60.3.9206.1533
	Thailand	T +662.207.3456	F +66.2207.3488
Worldwide Hotline		T +1.607.786.8131	F +1.607.786.8309
		T +1.800.295.2392	



Momentive Performance Materials 22 Corporate Woods Boulevard Albany, NY 12211

*Silquest, Silquest A-171 and SPUR+ are trademarks of Momentive Performance Materials Inc. Momentive is a trademark of Momentive Performance Materials Holdings LLC. Copyright 2008-2011 Momentive Performance Materials Inc. All rights reserved.

MOM-112-133-10E-GL 02/11 Printed in U.S.A.

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GMBH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (I) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.